

421 Stretch Tecvin

Rev. 6

Uso recomendado /
Recommended end-use:
CAZADORA Y PANTALÓN
ELÁSTICOS /
ELASTIC JACKETS & PANTS

Composición / Composition:
55% M-Aramida / M-Aramide
20% Viscosa FR / FR Viscose
20% Poliamida / Polyamide
4% Elastómero / Elastomer
1% Antiestático / Antistatic



421 Stretch Tecvin

LIGAMENTO / LIGAMENT	Sarga / Twill	
PESO / WEIGHT (gr/m²)	205 ± 5%	UNE 40339
ANCHO / WIDTH (cm)	160 ± 5	
ENCOGIMIENTO AL LAVADO WASHING SHRINKAGE	3%	UNE-EN ISO 15797
PILLING MARTINDALE (5000 cycles)	4	EN 12945-2
PRETRATAMIENTO / PRE-TREATMENT	50 washes	
RESISTENCIA A LA TRACCIÓN (N U x T) TENSILE STRENGTH (N W x F)	880 ± 5% 820 ± 5%	UNE-EN ISO 13934-1
INFLAMABILIDAD INFLAMMABILITY	A1- A2	EN 15025 (EN 11612)
CALOR CONVECTIVO CONVECTIVE HEAT	B1	ISO 9151
CALOR RADIANTE RADIANT HEAT	C1	ISO 6942
CALOR POR CONTACTO CONTACT HEAT	F1	EN ISO 12127-1
ANTIESTÁTICO ANTISTATIC	Pass	EN 11149/3/5
ARCO ELÉCTRICO ELECTRIC ARC	ATPV: 5,9 cal/cm² ELIM: 5,1 cal/cm²	EN 61482-1-1


421 Stretch Tecvin

Rev. 6

Sectores recomendados / Recommended use:



Petróleo y gas
Oil & Gas



Electricidad
Electricity



Policia
Policemen



Militar
Army

Normativas para prenda / Standard for garments:



Instrucciones de lavado EN 15797 (75°C) / Washing instructions EN 15797 (75°C) :



Colores disponibles / Available colors:



Marino 60
Navy Blue 60