

# 421 Stretch Tecvin

Rev. 8

Uso recomendado /  
Recommended end-use:  
CAZADORA Y PANTALÓN  
ELÁSTICOS /  
ELASTIC JACKETS & PANTS

Composición / Composition:  
55% M-Aramida / M-Aramide  
20% Viscosa FR / FR Viscose  
20% Poliamida / Polyamide  
4% Elastómero / Elastomer  
1% Antiestático / Antistatic



421 Stretch Tecvin

|                                                                   |                                        |                             |
|-------------------------------------------------------------------|----------------------------------------|-----------------------------|
| LIGAMENTO / LIGAMENT                                              | Sarga / Twill                          |                             |
| PESO / WEIGHT (gr/m²)                                             | 205 ± 5%                               | EN 12127                    |
| ANCHO / WIDTH (cm)                                                | 160 ± 5                                |                             |
| ENCOGIMIENTO AL LAVADO<br>WASHING SHRINKAGE                       | 3%                                     | EN ISO 15797 / EN ISO 5077  |
| PILLING MARTINDALE (5000 cycles)                                  | 4                                      | EN ISO 12945-2              |
| PRETRATAMIENTO / PRE-TREATMENT                                    | 50 washes                              |                             |
| RESISTENCIA A LA TRACCIÓN (N U x T)<br>TENSILE STRENGTH (N W x F) | 880 ± 5%<br>820 ± 5%                   | EN ISO 13934-1              |
| INFLAMABILIDAD<br>INFLAMMABILITY                                  | A1- A2                                 | EN ISO 15025 (EN ISO 11612) |
| CALOR CONVECTIVO<br>CONVECTIVE HEAT                               | B1                                     | EN ISO 9151                 |
| CALOR RADIANTE<br>RADIANT HEAT                                    | C1                                     | EN ISO 6942                 |
| CALOR POR CONTACTO<br>CONTACT HEAT                                | F1                                     | EN ISO 12127-1              |
| ANTIESTÁTICO<br>ANTISTATIC                                        | Pass                                   | EN 1149-3/5                 |
| ARCO ELÉCTRICO<br>ELECTRIC ARC                                    | ATPV: 5,9 cal/cm²<br>ELIM: 5,1 cal/cm² | EN IEC 61482-1-1            |


# 421 Stretch Tecvin

Rev. 8

Sectores recomendados / Recommended use:



Petróleo y gas  
Oil & Gas



Electricidad  
Electricity



Policia  
Policemen



Militar  
Army

Normativas para prenda / Standard for garments:



Instrucciones de lavado EN ISO 15797 (75°C) / Washing instructions EN ISO 15797 (75°C) :



\*Evitar utilizar suavizantes / Avoid using softeners

Colores disponibles / Available colors:



**Marino 60**  
Navy Blue 60

