

455 Silver Tecvin

Rev. 7

Uso recomendado /
Recommended end-use:
PRENDAS ALUMINIZADAS
/ ALUMINIZED GARMENTS

Composición / Composition:
50% Viscosa FR / FR Viscose
23% M-Aramida / M-Aramide
22% Aluminio /Aluminium
5% P-Aramida / P-Aramide



455 Silver Tecvin

LIGAMENTO / LIGAMENT		1EI / Tafetan	
PESO / WEIGHT (gr/m²)		550 ± 5%	EN 12127
ANCHO / WIDTH (cm)		150 ± 3	
RESISTENCIA A LA TRACCIÓN (N U x F) TENSILE STRENGTH (N W x F)		1095 ± 5% 1250 ± 5%	EN ISO 13934-1
RESISTENCIA AL DESGARRO (N U x F) TEAR STRENGTH (N W x F)		60 ± 5% 80 ± 5%	EN ISO 13937-2
ENCOGIMIENTO AL LAVADO WASHING SHRINKAGE		3%	EN ISO 6330 / EN ISO 5077
PRETRATAMIENTO / PRE-TREATMENT		Standard requirement	
INFLAMABILIDAD / INFLAMMABILITY		A2	EN ISO 15025 (EN ISO 11612)
CALOR CONVECTIVO / CONVECTIVE		B1	EN ISO 9151
CALOR RADIANTE / RADIANT		C2	EN ISO 6942
CALOR POR CONTACTO / CONTACT HEAT		F1	EN ISO 12127-1
RESIST. A GRAN SALPICADURAS. BIG SPLASH RESIST.	ALUMINIO / ALUMINIUM (780°C)	D3	EN ISO 9185:2025
	HIERRO / IRON (1400°C)	E3	EN ISO 9185:2007

455 Silver Tecvin

Rev. 7

Sectores recomendados / Recommended use:



Fundiciones (Fe/Zn/Cu/Al/Criolita)
Foundries (Fe/Zn/Cu/Al/Cryolite)

Normativas para prenda / Standard for garments:



Instrucciones de lavado EN ISO 6330 (30°C) / Washing instructions EN ISO 6330 (30°C) :



*Evitar utilizar suavizantes / Avoid using softeners

Colores disponibles / Available colors:



Plata
Silver