

470 Rip-Stop Tecvin

Rev. 9

Uso recomendado /
Recommended end-use:
CAZADORA, CAMISERIA Y
PANTALÓN /
JACKET, SHIRTS & PANTS

Composición / Composition:
64% Viscosa FR / FR Viscose
30% M-aramida / M-Aramide
5% P-Aramida / P- Aramide
1% Antiestático /Antistatic



470 Rip-Stop Tecvin

LIGAMENTO / LIGAMENT		Sarga / Twill	
PESO / WEIGHT (gr/m²)		265 ± 5%	UNE 40339
ANCHO / WIDTH (cm)		160 ± 3	
PILLING MARTINDALE (5.000 cycles)		4-5	EN 12945-2
ENCOGIMIENTO AL LAVADO WASHING SHRINKAGE		3%	EN 6330
PRETRATAMIENTO / PRE-TREATMENT		50 washes	
RESISTENCIA A LA TRACCIÓN (N U x T) TENSILE STRENGTH (N W x F)	1100 ± 5%	970 ± 5%	UNE-EN ISO 13934-1
	710 ± 5%	720 ± 5%	
RESISTENCIA AL DESGARRO (N U x T) TEAR STRENGTH (N W x F)	51 ± 5%	31 ± 5%	UNE-EN ISO 13937-2
	41 ± 5%	27 ± 5%	
INFLAMABILIDAD / INFLAMMABILITY	A1-A2	A1-A2	EN ISO25 (EN 11612)
CALOR CONVECTIVO / CONVECTIVE HEAT	B1	B1	ISO 9151
CALOR RADIANTE / RADIANT HEAT	C1	C1	ISO 6942
CALOR POR CONTACTO / CONTACT HEAT	F1	F1	EN ISO 12127-1
RESISTENCIA AL VAPOR DE AGUA WATER VAPOUR RESISTANCE (RET)	Pass	Pass	ISO 11092
RESISTENCIA TÉRMICA THERMAL RESISTANCE (RCT)	Pass	Pass	ISO 11092
ANTIESTÁTICO / ANTISTATIC	Pass	Pass	EN 1149-3-5
ARCO ELÉCTRICO / ELECTRIC ARC	4 kA APC 1	4 kA APC 1	EN 61482-1-2

470 Rip-Stop Tecvin

Rev. 9

Sectores recomendados / Recommended use:



Cristalera
Glass Foundry



Cementeras
Cement Plant


Normativas para prenda / Standard for garments:



Instrucciones de lavado EN 6330 (60°C) / Washing instructions EN 6330 (60°C):



Colores disponibles / Available colors:



Azul A028
Blue A028



Verde I016
Green I016

Ofrecemos el servicio de tinter colores especiales y una cantidad mínima de 300 m por color.
We have a special color dyeing service and a minimum quantity of 300 m.

