

816 Xispal RS

Rev. 9

Uso recomendado /
Recommended end-use:
CAMISETA INTERIOR /
T-SHIRT & KNITTED
UNDERWEAR

Composición / Composition:

50% Algodón / Cotton

39% Acrílica modificada tipo-F / Modified acrylic fibre type-F

10% Viscosa / Viscose

1% Antiestático / Antistatic



816 Xispal RS

LIGAMENTO / LIGAMENT		Punto liso / Knit	
PESO / WEIGHT (gr/m ²)	160 ± 5%	UNE 40339	
ANCHO / WIDTH (cm)	160 ± 5		
PILLING MARTINDALE (5.000 cycles)	4	EN 12945-2	
ENCOGIMIENTO AL LAVADO WASHING SHRINKAGE	5%	EN 6330	
PRETRATAMIENTO / PRE-TREATMENT	Standard requirement	50 washes	
INFLAMABILIDAD INFLAMMABILITY	A1-A2	A1-A2	EN 15025 (EN 11612)
CALOR CONVECTIVO CONVECTIVE HEAT	B1	B1	ISO 9151
CALOR RADIANTE RADIANT HEAT	C1	C1	ISO 6942
CALOR POR CONTACTO CONTACT HEAT	F1	F1	EN ISO 12127-1
ARCO ELÉCTRICO / ELECTRIC ARC	ATPV: Category I		ASTM F1959 (NFPA 70 E)
	ATPV: 6,40 cal/cm² ELIM: 4,80 cal/cm² 4kA APC 1	ATPV: 6,94 cal/cm² ELIM: 6,10 cal/cm² 4kA APC 1	EN 61482-1-1 EN 61482-1-2
ANTIESTÁTICO / ANTISTATIC	Pass	Pass	EN 1149/3/5


816 Xispal RS

Rev. 9

Sectores recomendados / Recommended use:



Petróleo y gas
Oil & Gas



Electricidad
Electricity



Policia
Policemen



Forestal
Forestmen



Bomberos
Firemen

Normativas para prenda / Standard for garments:



Instrucciones de lavado EN 6330 (40°C) / Washing instructions EN 6330 (40°C):



*Evitar utilizar suavizantes / Avoid using softeners

Colores disponibles / Available colors:



Naranja 20
Orange 20



Gris 80
Grey 80



Gris 82
Grey 82



Marino 60
Navy Blue 60

Ofrecemos el servicio de tinter colores especiales y una cantidad mínima de 300 m por color.
We have a special color dyeing service and a minimum quantity of 300 m.



STANDARD
100

2008AN2098
AITEX