

817 R1 Stretch Xispal RS

Rev.10

Uso recomendado /
Recommended end-use:
CAMISA ELÁSTICA /
ELASTIC SHIRT

Composición / Composition:
29% Acrílica modificada tipo-F / Modified acrylic fibre type-F
28% Viscosa / Viscose
19% Algodón / Cotton
19% Poliamida / Polyamide
4% Elastómero / Elastomer
1% Antiestático / Antistatic



817 R1 Stretch Xispal RS

LIGAMENTO / LIGAMENT		IE1 / Tafetan	
PESO / WEIGHT (gr/m²)	170 ± 5%	UNE 40339	
ANCHO / WIDTH (cm)	160 ± 5		
PILLING MARTINDALE (5.000 cycles)	5	EN 12945-2	
ENCOGIMIENTO AL LAVADO WASHING SHRINKAGE	3%	UNE-EN ISO 15797	
RESISTENCIA A LA TRACCIÓN (N U x T) TENSILE STRENGTH (N W x F)	400 ± 5% 350 ± 5%	UNE-EN 13934-1	
PRETRATAMIENTO / PRE-TREATMENT	Standard requirement	50 washes	
INFLAMABILIDAD / INFLAMMABILITY	A1-A2	A1-A2	EN 15025 (EN 11612)
CALOR CONVECTIVO / CONVECTIVE HEAT	B1	B1	ISO 9151
CALOR RADIANTE / RADIANT HEAT	C1	C1	ISO 6942
CALOR POR CONTACTO / CONTACT HEAT	F1	F1	EN ISO 12127-1
ARCO ELÉCTRICO / ELECTRIC ARC	No tested	ATPV: 6,4 cal/cm²	EN 61482-1-1
	No tested	ELIM: 5,8 cal/cm² 4kA APC I	EN 61482-1-2
ANTIÁCIDO / ANTACID (opcional/optional)*	Pass	Pass	EN 13034
ALTA VISIBILIDAD / HIGH VISIBILITY	Pass	No tested	EN 20471
ANTIESTÁTICO / ANTISTATIC	Pass	Pass	EN 1149/3/5

* Prendas antiácidas: polimerizar 2 minutos a 160°C o aditivar con acabado fluorocarbonado tras cada ciclo de lavado.
Antacid garments: polymerize 2 minutes at 160°C or add fluorocarbon finish after each washing cycle.

817 R1 Stretch Xispal RS

Rev. 10


Sectores recomendados / Recommended use:



Bomberos
Firemen



Petróleo y gas
Oil & Gas



Electricidad
Electricity



Policía
Policemen



Petroquímicas
Petrochemistry

Normativas para prenda / Standard for garments:



Instrucciones de lavado EN 15797 (75°C) / Washing instructions EN 15797 (75°C):



Colores disponibles / Available colors:



Amarillo HV
Yellow HV



Marino 70
Navy Blue 70

Ofrecemos el servicio de tinter colores especiales y una cantidad mínima de 300 m por color.
We have a special color dyeing service and a minimum quantity of 300 m.

Tejido para EPI (Equipo de Protección Individual) / PPE fabric (Personal Protective

Según reglamento UE 2024/2462 de 19/9/2024 se ha permitido el uso de ciertos compuestos del ácido undecafluorohexanoico (PFHxA) y sus sales para los equipos de protección individual destinados a proteger los usuarios contra riesgos incluidos en el ámbito de aplicación de la categoría de riesgo III, letras a), c) a f), h) y l) del Anexo I del Reglamento (UE) 2016/425.

According to EU Regulation 2024/2462 of 19/9/2024, the use of certain compounds of undecafluorohexanoic acid (PFHxA) and its salts has been permitted for personal protective equipment intended to protect users against risks included in the scope of risk category III, letters a), c) to f), h) and l) of Annex I to Regulation (EU) 2016/425.

