

826 R1 Xispal RS

Rev. 8

Uso recomendado /
Recommended end-use:
CAMISETAS Y PRENDAS
INTERIORES INVIERNO /
WINTER KNITTED
UNDERWEAR & T-SHIRT

Composición / Composition:
30% Acrílica modificada tipo-F / Modified acrylic fibre type-F
30% Viscosa / Viscose
20% Algodón / Cotton
19% Poliamida / Polyamide
1% Antiestático / Antistatic



826 R1 Xispal RS

LIGAMENTO / LIGAMENT		Interlock / Knit	
PESO / WEIGHT (gr/m²)		260 ± 5%	UNE 40339
ANCHO / WIDTH (cm)		160 ± 5	
ENCOGIMIENTO AL LAVADO WASHING SHRINKAGE		5%	UNE-EN ISO 6330
PRETRATAMIENTO / PRE-TREATMENT	Standard requirement	50 washes	
INFLAMABILIDAD / INFLAMMABILITY	A1-A2	A1-A2	EN ISO25 (EN 11612)
CALOR CONVECTIVO / CONVECTIVE	B1	B1	ISO 9151
CALOR RADIANTE / RADIANT HEAT	C1	C1	ISO 6942
CALOR POR CONTACTO / CONTACT HEAT	F1	F1	EN ISO 12127-1
ANTIESTÁTICO / ANTISTATIC	Pass	Pass	EN 1149/3/5
ARCO ELÉCTRICO / ELECTRIC ARC	ATPV: Category II	No tested	ASTM F1959 (NFPA 70E)
	No tested	ATPV: 14 cal/cm² ELIM: 11 cal/cm²	EN 61482-1-1
	4kA APC 1	No tested	EN 61482-1-2
ALTA VISIBILIDAD / HIGH VISIBILITY	Pass	No tested	EN 20471


826 R1 Xispal RS

Rev. 8

Sectores recomendados / Recommended use:



Petróleo y gas
Oil & Gas



Electricidad
Electricity



Petroquímicas
Petrochemistry



Bomberos
Firemen



Policia
Policemen

Normativas para prenda / Standard for garments:



Instrucciones de lavado EN 6330 (40°C) / Washing instructions EN 6330 (40°C):



*Evitar utilizar suavizantes / Avoid using softeners

Colores disponibles / Available colors:



Amarillo HV
HV Yellow



Gris 80
Grey 80



Marino 60
Navy Blue 60

Ofrecemos el servicio de tinter colores especiales y una cantidad mínima de 300 m por color.
We have a special color dyeing service and a minimum quantity of 300 m.



STANDARD
100



2008AN2098
AITEX