

# 828 Acolchado Xispal RS

Rev. 6

Uso recomendado /  
Recommended end-use:  
TEJIDOS ACOLCHADOS /  
QUILTED FABRIC

Composición / Composition:

42% **Aramida reciclada / Recycled aramid**

29% **Algodón / Cotton**

22,5% **Acrílica modificada tipo-F / Modified acrylic fibre type-F**

6% **Viscosa / Viscose**

0,5% **Antiestático / Antistatic**



LIGAMENTO / LIGAMENT	IEI Acolchado / Quilted Tafetan	
PESO / WEIGHT (gr/m <sup>2</sup> )	250 ± 5%	UNE 40339
ANCHO / WIDTH (cm)	150 ± 3	
ENCOGIMIENTO AL LAVADO WASHING SHRINKAGE	5%	UNE-EN ISO 6330
PRETRATAMIENTO / PRE-TREATMENT	Standard requirement	
INFLAMABILIDAD INFLAMMABILITY	A1	EN 15025 (EN 11612)
RESISTENCIA AL CALOR (180°C) HEAT RESISTANCE (180°C)	Pass	EN 17493
ANTIESTÁTICO ANTISTATIC	Pass	EN 1149/3/5



# 828 Acolchado Xispal RS


Rev. 6




Sectores recomendados / Recommended use:

FORRO ACOLCHADO / PADDED LINING

Normativas para prenda / Standard for garments:



Instrucciones de lavado EN 6330 (40°C) / Washing instructions EN 6330 (40°C):



\*Evitar utilizar suavizantes / Avoid using softeners

Colores disponibles / Available colors:



**Negro G328**  
Black G328