

830 Xispal RS

Rev. 8

Uso recomendado /
Recommended end-use:
CAZADORA Y PANTALÓN /
JACKET & PANTS

Composición / Composition:

50% Algodón / Cotton
39% Acrílica modificada tipo-F / Modified acrylic fibre type-F
10% Viscosa / Viscose
1% Antistático / Antistatic



830 Xispal RS

LIGAMENTO / LIGAMENT	3/2 b4,1 / Sateen		
PESO / WEIGHT (gr/m ²)	300 ± 5%	UNE 40339	
ANCHO / WIDTH (cm)	160 ± 3		
PILLING MARTINDALE (5.000 cycles)	5	EN 12945-2	
ENCOGIMIENTO AL LAVADO WASHING SHRINKAGE	3%	UNE-EN ISO 15797	
PRETRATAMIENTO / PRE-TREATMENT	Standard requirement	50 washes	
RESISTENCIA A LA TRACCIÓN (N U x T) TENSILE STRENGTH (N W x F)	1200 ± 5% 600 ± 5%	1100 ± 5% 700 ± 5%	UNE-EN 13934-1
INFLAMABILIDAD / INFLAMMABILITY	A1-A2	A1-A2	EN 15025 (EN 11612)
CALOR CONVECTIVO / CONVECTIVE HEAT	B1	B1	ISO 9151
CALOR RADIANTE / RADIANT HEAT	C1	C1	ISO 6942
RESIST. A GRAN SALPICADURA. BIG SPLASH RESIST.	ALUMINIUM (780°C)	D1	ISO 9185
	IRON (1400°C)	E2	ISO 9185
CALOR POR CONTACTO / CONTACT HEAT	F1	F1	EN ISO 12127-1
SOLDADURA / WELDING	Class 1	Class 1	EN 11611
ARCO ELÉCTRICO / ELECTRIC ARC	ATPV: 12,10 cal/cm ² ATPV: 12,0 cal/cm ² ELIM: 9,0 cal/cm ² 4rA APC 1	No tested No tested No tested 4rA APC 1	ASTM F1959 (NFPA 70E) EN 61482-1-1 EN 61482-1-2
ANTIESTÁTICO / ANTISTATIC	Pass	Pass	EN 1149/3/5
ANTIÁCIDO / ANTIACID (opcional/optional)*	Pass	No tested	EN 13034
ALTA VISIBILIDAD / HIGH VISIBILITY	Pass ¹	Pass ¹	EN 20471

*Prendas antiácidas: polimerizar 2 minutos a 160°C o aditivar con acabado fluorocarbonado tras cada ciclo de lavado.
Antacid garments: polymerize 2 minutes at 160°C or add fluorocarbon finish after each washing cycle.

¹Condiciones de lavado EN 6330 (60°C) / Washing instructions EN 6330 (60°C)

830 Xispal RS

Rev. 8


Sectores recomendados / Recommended use:



Fundiciones (Fe/Al)
Foundries (Fe/Al)



Petróleo y gas
Oil & Gas



Electricidad
Electricity



Soldadura
Welding



Petroquímicas
Petrochemistry

Normativas para prenda / Standard for garments:



Instrucciones de lavado EN 15797 (75°C) / Washing instructions EN 15797 (75°C):



Colores disponibles / Available colors:



Amarillo HV
HV Yellow



Naranja 20
Orange 20




Rojo 30
Red 30



Gris 80
Grey 80



Gris 82
Grey 82



Azulina 50
Royal Blue 50



Marino 70
Navy Blue 70



Marino 60
Navy Blue 60

Ofrecemos el servicio de tinter colores especiales y una cantidad mínima de 300 m por color.
We have a special color dyeing service and a minimum quantity of 300 m.



STANDARD
100

2008AN2098
AITEK