

834 R1 Xispal RS

Rev. 9

Uso recomendado /
Recommended end-use:
CAZADORA Y PANTALÓN /
JACKET & PANTS

Composición / Composition:

42% Algodón / Cotton
41% Acrílica modificada tipo-F / Modified acrylic fibre type-F
10% Viscosa / Viscose
6% Poliamida / Polyamide
1% Antiestático / Antistatic



834 R1 Xispal RS

LIGAMENTO / LIGAMENT		3/2 b4,1/ Sateen	
PESO / WEIGHT (gr/m ²)		340 ± 5%	UNE 40339
ANCHO / WIDTH (cm)		160 ± 3	
PILLING MARTINDALE (5,000 cycles)		5	EN 12945-2
ENCOGIMIENTO AL LAVADO WASHING SHRINKAGE		3%	UNE-EN ISO 15797
PRETRATAMIENTO / PRE-TREATMENT		Standard requirement	50 washes
RESISTENCIA A LA TRACCIÓN (N U x T) TENSILE STRENGTH (N W x F)		1800 ± 5% 1100 ± 5%	1600 ± 5% 1000 ± 5% UNE-EN 13934-1
INFLAMABILIDAD / INFLAMMABILITY		A1-A2	A1-A2 EN 15025 (EN 11612)
CALOR CONVECTIVO / CONVECTIVE		B1	B1 ISO 9151
CALOR RADIANTE/ RADIANT HEAT		C1	C1 ISO 6942
RESIST. A GRAN SALPICADURA. BIG SPLASH RESIST.	ALUMINIUM (780°C)	D2	D2 ISO 9185
	IRON (1400°C)	E2	E3 ISO 9185
CALOR POR CONTACTO / CONTACT HEAT		F1	F1 EN ISO 12127-1
SOLDADURA / WELDING		Class 2	Class 1 EN 11611
ANTIÁCIDO / ANTACID (opcional/optional)*		Pass	Pass EN 13034
ARCO ELÉCTRICO / ELECTRIC ARC		ATPV: Category II 4rA APC I	No tested 4rA APC I ASTM F1959 (NFPA 70E) EN 61482-1-2
ALTA VISIBILIDAD / HIGH VISIBILITY ¹		Pass	Pass EN 20471
ANTIESTÁTICO / ANTISTATIC		Pass	Pass EN 1149/3/5

*Prendas antiácidas: polimerizar 2 minutos a 160°C o aditivar con acabado fluorocarbonado tras cada ciclo de lavado.
Antacid garments: polymerize 2 minutes at 160°C or add fluorocarbon finish after each washing cycle.

¹Condiciones de lavado EN 6330 (60°C) / Washing instructions EN 6330 (60°C)

834 R1 Xispal RS

Rev. 9


Sectores recomendados / Recommended use:



Cementeras
Cement Plant



Fundiciones (Fe/Al)
Foundries (Fe/Al)



Electricidad
Electricity



Soldadura
Welding

Normativas para prenda / Standard for garments:



Instrucciones de lavado EN 15797 (75°C) / Washing instructions EN 15797 (75°C):



Colores disponibles / Available colors:



Naranja 20
Orange 20



Gris 80
Grey 80



Marino 70
Navy Blue 70

Ofrecemos el servicio de tinter colores especiales y una cantidad mínima de 300 m por color.
We have a special color dyeing service and a minimum quantity of 300 m.

Tejido para EPI (Equipo de Protección Individual) / PPE fabric (Personal Protective

Según reglamento UE 2024/2462 de 19/9/2024 se ha permitido el uso de ciertos compuestos del ácido undecafluorohexanoico (PFHxA) y sus sales para los equipos de protección individual destinados a proteger los usuarios contra riesgos incluidos en el ámbito de aplicación de la categoría de riesgo III, letras a), c) a f), h) y l) del Anexo I del Reglamento (UE) 2016/425.

According to EU Regulation 2024/2462 of 19/9/2024, the use of certain compounds of undecafluorohexanoic acid (PFHxA) and its salts has been permitted for personal protective equipment intended to protect users against risks included in the scope of risk category III, letters a), c) to f), h) and l) of Annex I to Regulation (EU) 2016/425.

