

945 Valen-t

Rev. 8

Uso recomendado /
Recommended end-use:
CAZADORA Y PANTALÓN /
JACKET & PANTS

Composición / Composition:
52% Algodón / Cotton
22% Acrílica modificada tipo-F / Modified acrylic fibre type-F
19% Viscosa / Viscose
6% P-Aramida / P-Aramide
1% Antiestático / Antistatic



945 Valen-t

LIGAMENTO / LIGAMENT		Broken Twill	
PESO / WEIGHT (gr/m²)		450 ± 5%	UNE 40339
ANCHO / WIDTH (cm)		160 ± 3	
PILLING MARTINDALE (5.000 cycles)		5	EN 12945-2
ENCOGIMIENTO AL LAVADO WASHING SHRINKAGE		3%	UNE-EN ISO 15797
PRETRATAMIENTO / PRE-TREATMENT		Standard requirement	50 washes
RESISTENCIA A LA TRACCIÓN (N U x T) TENSILE STRENGTH (N W x F)		1600 ± 5% 1200 ± 5%	1500 ± 5% 1200 ± 5% UNE-EN 13934-1
INFLAMABILIDAD / INFLAMMABILITY		A1-A2	A1-A2 EN 15025 (EN 11612)
CALOR CONVECTIVO / CONVECTIVE HEAT		B1	B1 ISO 9151
CALOR RADIANTE / RADIANT HEAT		C1	C1 ISO 6942
RESIST. A GRAN SALPICADURA. BIG SPLASH RESIST.	ALUMINIUM (780°C)	D3	D2 ISO 9185
	IRON (1400°C)	E3	E3 ISO 9185
CALOR POR CONTACTO / CONTACT HEAT		No tested	F1 EN ISO 12127-1
SOLDADURA / WELDING		No tested	Class 2 EN 11611
ARCO ELÉCTRICO / ELECTRIC ARC		ATPV: 15,30 cal/cm²	No tested ASTM F1959 (NFPA 70E)
		ATPV: 18,00 cal/cm²	No tested EN 61482-1-1
		ELIM: 13,00 cal/cm² 7rA APC 2	No tested EN 61482-1-2
ALTA VISIBILIDAD / HIGH VISIBILITY		Pass	Pass ¹ EN 20471
ANTIESTÁTICO / ANTISTATIC		Pass	Pass EN 1149/3/5
ANTIÁCIDO / ANTIACID (opcional/optional)*		Pass	No tested EN 13034


*Prendas antiácidas: polimerizar 2 minutos a 160°C o aditivar con acabado fluorocarbonado tras cada ciclo de lavado.
Antacid garments: polymerize 2 minutes at 160°C or add fluorocarbon finish after each washing cycle.

¹Condiciones de lavado EN 6330 (60°C) / Washing instructions EN 6330 (60°C).

945 Valen-t

Rev. 8

Sectores recomendados / Recommended use:



Electricidad
Electricity



Fundiciones (Fe/Zn/Cu/Al/Criolite)
Foundries (Fe/Zn/Cu/Al/Criolite)



Soldadura
Welding



Cementeras
Cement Plant

Normativas para prenda / Standard for garments:



Instrucciones de lavado EN 15797 (75°C) / Washing instructions EN 15797 (75°C):



Colores disponibles / Available colors:



Naranja 20
Orange 20



Marino 70
Navy Blue 70

Ofrecemos el servicio de tinter colores especiales y una cantidad mínima de 300 m por color.
We have a special color dyeing service and a minimum quantity of 300 m.



STANDARD
100



2008AN2098
AITEX