

945 Valen-t

Rev. 10

Uso recomendado /
Recommended end-use:
CAZADORA Y PANTALÓN /
JACKET & PANTS

Composición / Composition:

52% Algodón / Cotton

22% Acrílica modificada tipo-F / Modified acrylic fibre type-F

19% Viscosa / Viscose

6% P-Aramida / P-Aramide

1% Antiestático / Antistatic



945 Valen-t

LIGAMENTO / LIGAMENT		Broken Twill	
PESO / WEIGHT (gr/m ²)		450 ± 5%	EN 12127
ANCHO / WIDTH (cm)		160 ± 3	
PILLING MARTINDALE (5.000 cycles)		5	EN ISO 12945-2
ENCOGIMIENTO AL LAVADO WASHING SHRINKAGE		3%	EN ISO 15797 / EN ISO 5077
PRETRATAMIENTO / PRE-TREATMENT		Standard requirement	50 washes
RESISTENCIA A LA TRACCIÓN (N U x T) TENSILE STRENGTH (N W x F)		1600 ± 5% 1200 ± 5%	1500 ± 5% 1200 ± 5% EN 13934-1
INFLAMABILIDAD / INFLAMMABILITY		A1-A2	A1-A2 EN ISO 15025 (EN ISO
CALOR CONVECTIVO / CONVECTIVE HEAT		B1	B1 EN ISO 9151
CALOR RADIANTE / RADIANT HEAT		C1	C1 EN ISO 6942
RESIST. A GRAN SALPICADURA. BIG SPLASH RESIST.	ALUMINIUM (780°C)	D3	D2 EN ISO 9185:2007
	IRON (1400°C)	E3	E3 EN ISO 9185:2007
CALOR POR CONTACTO / CONTACT HEAT		No tested	F1 EN ISO 12127-1
SOLDADURA / WELDING		No tested	Class 2 EN ISO 11611
ARCO ELÉCTRICO / ELECTRIC ARC		ATPV: Category II ATPV: 18,00 cal/cm ² ELIM: 13,00 cal/cm ² 7kA APC 2	No tested No tested No tested 7kA APC 2 ASTM F1959 (NFPA 70E) EN IEC 61482-1-1 EN IEC 61482-1-2
ALTA VISIBILIDAD / HIGH VISIBILITY		Pass	Pass ¹ EN ISO 20471
ANTIESTÁTICO / ANTISTATIC		Pass	Pass EN 1149-3/5
ANTIÁCIDO / ANTIACID (opcional/optional)*		Pass	No tested EN 13034


*Prendas antiácidas: polimerizar 2 minutos a 160°C o aditivar con acabado fluorocarbonado tras cada ciclo de lavado.
Antacid garments: polymerize 2 minutes at 160°C or add fluorocarbon finish after each washing cycle.

¹Condiciones de lavado EN ISO 6330 (60°C) / Washing instructions EN ISO 6330

945 Valen-t

Rev. 10

Sectores recomendados / Recommended use:



Electricidad
Electricity



Fundiciones (Fe/Zn/Cu/Al/Criolita)
Foundries (Fe/Zn/Cu/Al/Cryolite)



Soldadura
Welding



Cementeras
Cement Plant

Normativas para prenda / Standard for garments:



Instrucciones de lavado EN ISO 15797 (75°C) / Washing instructions EN ISO 15797 (75°C):



Colores disponibles / Available colors:



Naranja 20
Orange 20



Marino 70
Navy Blue 70

Ofrecemos el servicio de tinter colores especiales y una cantidad mínima de 300 m por color.
We have a special color dyeing service and a minimum quantity of 300 m.

Tejido para EPI (Equipo de Protección Individual) / PPE fabric (Personal Protective

Según reglamento UE 2024/2462 de 19/9/2024 se ha permitido el uso de ciertos compuestos del ácido undecafluorohexanoico (PFHxA) y sus sales para los equipos de protección individual destinados a proteger los usuarios contra riesgos incluidos en el ámbito de aplicación de la categoría de riesgo III, letras a), c) a f), h) y l) del Anexo I del Reglamento (UE) 2016/425.

According to EU Regulation 2024/2462 of 19/9/2024, the use of certain compounds of undecafluorohexanoic acid (PFHxA) and its salts has been permitted for personal protective equipment intended to protect users against risks included in the scope of risk category III, letters a), c) to f), h) and l) of Annex I to Regulation (EU) 2016/425.

