

# 455 Silver Tecvin

Rev. 5

Uso recomendado /  
Recommended end-use:  
PRENDAS ALUMINIZADAS /  
ALUMINIZED GARMENTS

Composición / Composition:  
**50% Viscosa FR / FR Viscose**  
**23% M-Aramida / M-Aramide**  
**22% Aluminio / Aluminium**  
**5% P-Aramida / P-Aramide**



455 Silver Tecvin

LIGAMENTO / LIGAMENT	IEI / Tafetan	
PESO / WEIGHT (gr/m <sup>2</sup> )	550 ± 5%	UNE 40339
ANCHO / WIDTH (cm)	150 ± 3	
RESISTENCIA A LA TRACCIÓN (N U x F) TENSILE STRENGTH (N W x F)	1200 ± 5% 1050 ± 5%	UNE-EN ISO 13934-1
RESISTENCIA AL DESGARRO (N U x F) TEAR STRENGTH (N W x F)	60 ± 5% 80 ± 5%	UNE-EN ISO 13937-2
ENCOGIMIENTO AL LAVADO WASHING SHRINKAGE	3%	UNE-EN ISO 6330
PRETRATAMIENTO / PRE-TREATMENT	Standard requirement	
INFLAMABILIDAD / INFLAMMABILITY	A2	EN 15025 (EN 11612)
CALOR CONVECTIVO / CONVECTIVE	B1	ISO 9151
CALOR RADIANTE / RADIANT	C2	ISO 6942
CALOR POR CONTACTO / CONTACT HEAT	F1	EN ISO 12127-1
RESIST. A GRAN SALPICADURAS. BIG SPLASH RESIST.	ALUMINIO / ALUMINIUM (780°C)	D3 ISO 9185
	HIERRO / IRON (1400°C)	E3 ISO 9185

# 455 Silver Tecvin

Rev. 5

Sectores recomendados / Recommended use:



Fundiciones (Fe/Zn/Cu/Al/Criolite)  
Foundries (Fe/Zn/Cu/Al/Criolite)

Normativas para prenda / Standard for garments:



Instrucciones de lavado EN 6330 (30°C) / Washing instructions EN 6330 (30°C) :



Colores disponibles / Available colors:



Silver