

458 Silver Tecvin (exp.)

Rev. 0

Recommended end-use /
Uso recomendado:
ALUMINIZED GARMENTS /
PRENDAS ALUMINIZADAS

Composition / Composición:
41% Pre-oxidated acrylic / Acrílica Pre-oxidada
17% P-Aramide / P-Aramida
20% Aluminium / Aluminio
22% Adhesive / Adhesivo



458 Silver Tecvin (exp.)

LIGAMENT LIGAMENTO		Broken Twill	
WEIGHT (oz sq yd) PESO (gr/m²)		17,11 ± 5% 580 ± 5%	EN 12127
WIDTH (in) ANCHO (cm)		59 ± 1,2 150 ± 3	
PRE-TREATMENT PRETRATAMIENTO		Standard requirement	
TENSILE STRENGTH (N W x F) RESISTENCIA A LA TRACCIÓN (N U x T)		2400 ± 5% 1950 ± 5%	EN ISO 13934-1
INFLAMMABILITY / INFLAMABILIDAD		A1-A2	EN ISO 15025 (EN ISO 11612)
CONVECTIVE HEAT / CALOR CONVECTIVO		B2	EN ISO 9151
RADIANT HEAT / CALOR RADIANTE (After flexion pretreatment)		C4	EN ISO 6942
CONTACT HEAT / CALOR POR CONTACTO		F1	EN ISO 12127-1
BIG SPLASH RESIST. RESIST. A GRAN SALPICADURA	IRON (2550 F / 1400°C)	E3	EN ISO 9185:2007

458 Silver Tecvin (exp.)

Rev. 0

Recommended use / Sectores recomendados:



Foundries (Fe)
Fundiciones (Fe)

Standard for garments / Normativas para prenda:



Washing instructions: Do not Wash / Instrucciones de lavado: No Lavar:



Available colors / Colores disponibles:



Silver
Plata