

# 918 Valen-t

Rev. 5

Recommended end-use /  
 Uso recomendado:  
 JACKET, SHIRT & PANTS,  
 COVERALL /  
 CAMISOLA, CAMISA Y  
 OVEROL

Composition / Composición:  
**35 % Modified acrylic fibre type-F / Acrílica modificada tipo-F**  
**30 % Cotton / Algodón**  
**20 % Viscose / Viscosa**  
**14 % P-Aramide / P-Aramida**  
**1 % Antistatic / Antiestático**



918 Valen-t

<b>LIGAMENT</b> <b>LIGAMENTO</b>	<b>Twill</b> <b>Sarga</b>		
<b>WEIGHT</b> (oz sq yd) <b>PESO</b> (gr/m <sup>2</sup> )	<b>5,31 ± 5%</b> <b>180 ± 5%</b>		UNE 40339
<b>WIDTH</b> (in) <b>ANCHO</b> (cm)	<b>63 ± 1,2</b> <b>160 ± 3</b>		
<b>TENSILE STRENGTH</b> (N W x F) <b>RESISTENCIA A LA TRACCIÓN</b> (N U x T)	<b>510 ± 5%</b> <b>250 ± 5%</b>		ASTM D5034 (ASTM F1506)
<b>TEAR EWSISTANCE</b> (N W x F) <b>RESISTENCIA AL RASGADO</b> (N U x T)	<b>35 ± 5%</b> <b>25 ± 5%</b>		ASTM D1424 (ASTM F1506)
<b>PILLING MARTINDALE</b> (5.000 cycles)	<b>4-5</b>		UNE-EN 12945-2
<b>WASHING SHRINKAGE</b> <b>ENCOGIMIENTO AL LAVADO</b>	<b>5%</b>		AATCC 135 (3, IV, A, iii)
<b>PRE-TREATMENT</b> <b>PRETRATAMIENTO</b>	<b>Standard requirements</b>	<b>100 washes</b>	
<b>HEAT RESISTANCE</b> <b>RESISTENCIA AL CALOR</b>	<b>Pass</b>	<b>No tested</b>	ASTM F2894 (NFPA 2112)
<b>VERTICAL FLAMMABILITY</b>	<b>Pass</b>	<b>Pass</b>	ASTM D6413 (NFPA 2112) ASTM F1506)
<b>HEAT TRANSFER PERFORMANCE (HTP)</b> <b>TRANSFERENCIA DE CALOR</b>	<b>Pass</b>	<b>No tested</b>	ASTM F2700 (NFPA 2112)
<b>FLASH FIRE EXPOSURE (%)</b> (Manikrin Test average 2° & 3° burn injury)	<b>27,60</b>	<b>No tested</b>	ASTM F1930 (NFPA 2112)
<b>HIGH VISIBILITY</b> <b>ALTA VISIBILIDAD</b>	<b>Pass</b>	<b>No tested</b>	ANSI 107
<b>ELECTRIC ARC</b> <b>ARCO ELECTRICO</b>	ATPV: <b>6,5 cal/cm<sup>2</sup></b> HAF: <b>68,8 %</b>	<b>No tested</b>	ASTM F 1506

MADE IN MEXICO


# 918 Valen-t

Rev. 5

Recommended use / Sectores recomendados:



Oil & Gas  
Petróleo y gas



Electricity  
Electricidad



Policemen  
Policía

Standard for garments / Normativas para prenda:



Washing instructions EN 15797 (167°F) / Instrucciones de lavado EN 15797 (75°C):



Available colors / Colores disponibles:



Khaki 412  
Khaki 412



Orange 20  
Naranja 20



Navy Blue 70  
Marino 70

We have a special color dyeing service and a minimum quantity of 600 m.  
Ofrecemos el servicio de tinter colores especiales y una cantidad minima de 600 m por color.