

919 Valen-t

Rev. 6

Recommended end-use /
Uso recomendado:
T-SHIRT & KNITTED
UNDERWEAR /
CAMISA INTERIOR

Composition / Composición:
35% Modified acrylic fibre type-F / Acrílica modificada tipo-F
30% Cotton / Algodón
20% Viscose / Viscosa
14% P-Aramide / P-Aramida
1% Antistatic / Antiestático



919 Valen-t

LIGAMENT LIGAMENTO	Knit Interlock		
WEIGHT (oz sq yd) PESO (gr/m²)	5,60 ± 5% 190 ± 5%	UNE 40339	
WIDTH (in) ANCHO (cm)	61 ± 2 155 ± 5		
BURST STRENGHT (kPa) RESISTENCIA AL ESTALLIDO	550 ± 5%	ASTM D3786 (ASTM F1506)	
PILLING MARTINDALE (5.000 cycles)	4-5	UNE EN 12945-2	
WASHING SHRINKAGE ENCOGIMIENTO AL LAVADO	5%	AATC 135 (3, IV, A, iii)	
ASTM			
PRE-TREATMENT PRETRATAMIENTO	Standard requirement	100 washes	
HEAT RESISTANCE RESISTENCIA AL CALOR	Pass	No tested	ASTM F2894 (NFPA 2112)
VERTICAL FLAMMABILITY IMFLABAMIBILIDAD VERTICAL	Pass	Pass	ASTM 6413 NFPA 2112 (ASTM 1506)
HEAT TRANSFER PERFORMANCE (HTP) TRANSFERENCIA DE CALOR	Pass	No tested	ASTM F2700 (NFPA 2112)
FLASH FIRE EXPOSURE (%) (Manikin Test average 2° & 3° burn injury)	16,4	No tested	ASTM F1930 (NFPA 2112)
ELECTRIC ARC ARCO ELÉCTRICO	ATPV: 8,8 cal/cm² HAF: 78,9%	No tested	ASTM F1959 (ASTM F1506)
HIGH VISIBILITY ALTA VISIBILIDAD	Pass	No tested	ANSI 107
UNE EN			
PRE-TREATMENT PRETRATAMIENTO	Standard requirement		
INFLAMMABILITY INFLAMABILIDAD	A1-A2	EN 15025 (EN 11612)	
CONVECTIVE HEAT CALOR CONVECTIVO	B1	ISO 9151	
RADIANT HEAT CALOR RADIANTE	C1	ISO 6942	
CONTACT HEAT CALOR POR CONTACTO	F1	EN ISO 12127-1	
ELECTRIC ARC ARCO ELÉCTRICO	ATPV: 11 cal/cm² ELIM: 9,9 cal/cm² 4kA APC I	EN 61482-1-1 EN 61482-1-2	
HIGH VISIBILITY ALTA VISIBILIDAD	Pass	EN 20471	
ANTISTATIC ANTIESTÁTICO	Pass	EN 1149/3/5	


919 Valen-t

Rev. 6

Recommended use / Sectores recomendados:



Oil & Gas
Petróleo y gas



Electricity
Electricidad

Standard for garments / Normativas para prenda:



Washing instructions EN 6330 (104°F) / Instrucciones de lavado EN 6330 (40°C):



*Avoid using softeners / Evitar utilizar suavizantes

Available colors / Colores disponibles:



Yellow HV
Amarillo HV



Navy Blue 60
Marino 60

We have a special color dyeing service and a minimum quantity of 400 Kg.
Ofrecemos el servicio de tinter colores especiales y una cantidad mínima de 400 Kg por color.