

334

Rev. 4

Uso recomendado /
Recommended end-use:
RECUBRIMIENTO DE CABLEADO /
WIRING COATING

Composición / Composition :
50% P-Aramida / P-Aramide
50 % Polyurethane / Poliuretano

LIGAMENTO / LIGAMENT	IEI / Tafetan	
PESO / WEIGHT (gr/m ²)	345 ± 5%	UNE 40339
ANCHO / WIDTH (cm)	120 ± 3	
PILLING MARTINDALE (5.000 cycles)	5	EN 12945-2
RESISTENCIA A LA TRACCIÓN (N U x T) TENSILE STRENGTH (N W x F)	3200 ± 5% 2900 ± 5%	UNE-EN ISO 13934-1
ENCOGIMIENTO AL LAVADO WASHING SHRINKAGE	3%	UNE-EN ISO 15797
INFLAMABILIDAD / INFLAMMABILITY	A1	EN 15025

Sectores recomendados / Recommended use:

INDUSTRIA

Normativas para prenda / Standard for garments:



Instrucciones de lavado EN 15797 (75°C) / Washing instructions EN 15797 (75°C):

