

356

Rev. 1

Recommended end-use /
Uso recomendado:
COVERS /
FUNDAS Y
RECUBRIMIENTOS

Composition / Composición:
75% P-Aramida / P-Aramide
25 % Siloxane metalizado / Metalized Siloxane

356

LIGAMENT LIGAMENTO	Twill / Sarga	
WEIGHT (oz sq yd) PESO (gr/m ²)	16,22 ± 5% 550 ± 5%	UNE 40339
WIDTH (in) ANCHO (cm)	51,18 ± 1,2 130 ± 3	
PILLING MARTINDALE (5.000 cycles)	5	EN 12945-2
TENSILE STRENGTH (N W x F) RESISTENCIA A LA TRACCIÓN (N U x T)	3400 ± 5% 3300 ± 5%	UNE-EN ISO 13934-1
WASHING SHRINKAGE ENCOGIMIENTO AL LAVADO	3%	UNE-EN ISO 15797
INFLAMMABILITY INFLAMABILIDAD	A1-A2	EN 15025

356

Rev. 1

Recommended use / Sectores recomendados:

AUTOMOTIVE

Standard for garments / Normativas para prenda:



Washing instructions EN 15797 (167°F) / Instrucciones de lavado EN 15797 (75°C):



Colores disponibles / Available colors:



Silver