

825R1 CL Xispal RS

Rev. 10

Recommended end-use /
Uso recomendado:
JACKET, PANTS & COVERALL
/ CAMISOLA, PANTALÓN Y
OVEROL

Composition / Composición:
33% Modified acrylic fibre type-F / Acrílica modificada tipo-F
30% Viscose / Viscosa
18% Cotton / Algodón
15% Polyamide / Poliamida
3% Aramide / Aramida
1% Antistatic / Antiestático



825R1 CL Xispal RS

LIGAMENT LIGAMENTO	Twill Sarga	
WEIGHT (oz sq yd) PESO (gr/m²)	7,40 ± 5% 250 ± 5%	EN 12127
WIDTH (in) ANCHO (cm)	63 ± 1,2 160 ± 3	
PILLING MARTINDALE (5.000 cycles)	5	EN ISO 12945-2
WASHING SHRINKAGE ENCOGIMIENTO AL LAVADO	5%	AATCC 135 (3, IV, A, iii)
ASTM		
PRE-TREATMENT PRETRATAMIENTO	Standard requirements	
TENSILE STRENGTH (N W x F) RESISTENCIA A LA TRACCIÓN (N U x T)	590 ± 5% 330 ± 5%	ASTM D5034 (ASTM F1506)
TEAR RESISTANCE (N W x F) RESISTENCIA AL RASGADO (N U x T)	58 ± 5% 54 ± 5%	ASTM D1424 (ASTM F1506)
HEAT RESISTANCE RESISTENCIA AL CALOR	Pass	ASTM F2894 (NFPA 2112)
VERTICAL FLAMMABILITY INFLAMABILIDAD VERTICAL	Pass	ASTM D6413 (NFPA 2112, ASTM F1506)
HEAT TRANSFER PERFORMANCE (HTP) TRANSFERENCIA DE CALOR	Pass	ASTM F2700 (NFPA 2112)
FLASH FIRE EXPOSURE (%) (Manikin Test average 2° & 3° burn injury)	9,84	ASTM F1930 (NFPA 2112)
ELECTRIC ARC ARCO ELECTRICO	ATPV: Category II	ASTM F 1959 (NFPA 70E)
HIGH VISIBILITY ALTA VISIBILIDAD	Pass	ANSI 107
UNE-EN		
PRE-TREATMENT PRETRATAMIENTO	Standard requirements	
ANTISTATIC ANTIESTÁTICO	Pass	EN 1149-3/5


825R1 CL Xispal RS

Rev. 10

Recommended use / Sectores recomendados:



Oil & Gas
Petróleo y gas



Electricity
Electricidad



Petrochemistry
Petroquímicas



Policemen
Policía

Standard for garments / Normativas para prenda:



Washing instructions: AATCC 135 (3, IV, A, iii) Washing Temp. (120°F) Drying Temp. (149°F)
Instrucciones de lavado: AATCC 135 (3, IV, A, iii) Temp. lavado (49°C) Temp. Secado (65°C)



Available colors / Colores disponibles:



Yellow HV
Amarillo HV



Navy Blue 70
Marino 70

We have a special color dyeing service and a minimum quantity of 600 m.
Ofrecemos el servicio de tintar colores especiales y una cantidad mínima de 600 m por color.