

816 Xispal RS

Rev. 8

Uso recomendado /
Recommended end-use:
CAMISETA INTERIOR /
T-SHIRT & KNITTED
UNDERWEAR

Composición / Composition:
50% Algodón / Cotton
39% Acrílica modificada tipo-F / Modified acrylic fibre type-F
10% Viscosa / Viscose
1% Antiestático / Antistatic



816 Xispal RS

LIGAMENTO / LIGAMENT		Punto liso / Knit	
PESO / WEIGHT (gr/m²)		160 ± 5%	UNE 40339
ANCHO / WIDTH (cm)		160 ± 5	
PILLING MARTINDALE (5.000 cycles)		4	EN 12945-2
ENCOGIMIENTO AL LAVADO WASHING SHRINKAGE		5%	EN 6330
PRETRATAMIENTO / PRE-TREATMENT		Standard requirement	50 washes
INFLAMABILIDAD INFLAMMABILITY		A1-A2	A1-A2 EN 15025 (EN 11612)
CALOR CONVECTIVO CONVECTIVE HEAT		B1	B1 ISO 9151
CALOR RADIANTE RADIANT HEAT		C1	C1 ISO 6942
CALOR POR CONTACTO CONTACT HEAT		F1	F1 EN ISO 12127-1
ARCO ELÉCTRICO / ELECTRIC ARC		ATPV: 4,10 cal/cm²	ASTM 1959 (NFPA 70 E)
		ATPV: 6,40cal/cm² ELIM: 4,80 cal/cm² 4kA APC I	ATPV: 6,94 cal/cm² ELIM: 6,10 cal/cm² 4kA APC I EN 61482-1-1 EN 61482-1-2
ANTIESTÁTICO / ANTISTATIC		Pass	Pass EN 1149/3/5


816 Xispal RS

Rev. 8

Sectores recomendados / Recommended use:



Petróleo y gas
Oil & Gas



Electricidad
Electricity



Policia
Policemen



Forestal
Forestmen



Bomberos
Firemen

Normativas para prenda / Standard for garments:



Instrucciones de lavado EN 6330 (40°C) / Washing instructions EN 6330 (40°C):



*Evitar utilizar suavizantes / Avoid using softeners

Colores disponibles / Available colors:



Naranja 20
Orange 20



Gris 80
Grey 80



Gris 82
Grey 82



Marino 60
Navy Blue 60

Ofrecemos el servicio de tinter colores especiales y una cantidad mínima de 300 m por color.
We have a special color dyeing service and a minimum quantity of 300 m.