

825 Xispal RS

Rev. 7

Uso recomendado /
Recommended end-use:
CAZADORA Y PANTALÓN /
JACKET & PANTS

Composición / Composition:

50% Algodón / Cotton

39% Acrílica modificada tipo-F / Modified acrylic fibre type-F

10% Viscosa / Viscose

1% Antiestático / Antistatic



825 Xispal RS

LIGAMENTO / LIGAMENT		Sarga / Twill	
PESO / WEIGHT (gr/m ²)		250 ± 5%	UNE 40339
ANCHO / WIDTH (cm)		160 ± 3	
PILLING MARTINDALE (5.000 cycles)		5	EN 12945-2
ENCOGIMIENTO AL LAVADO / WASHING SHRINKAGE		3%	UNE-EN ISO 15797
PRETRATAMIENTO / PRE-TREATMENT		Standard requirement	50 washes
RESISTENCIA A LA TRACCIÓN (N U x T) TENSILE STRENGTH (N W x F)		900 ± 5% 450 ± 5%	800 ± 5% 500 ± 5% UNE-EN 13934-1
INFLAMABILIDAD / INFLAMMABILITY		A1-A2	A1-A2 EN 15025 (EN 11612)
CALOR CONVECTIVO / CONVECTIVE HEAT		B1	B1 ISO 9151
CALOR RADIANTE / RADIANT HEAT		C1	C1 ISO 6942
RESIST. A GRAN SALPICADURA. BIG SPLASH RESIST.	ALUMINIUM (780°C)	D1	D1 ISO 9185
	IRON (1400°C)	E1	E1 ISO 9185
CALOR POR CONTACTO / CONTACT HEAT		F1	F1 EN ISO 12127-1
SOLDADURA / WELDING		Class 1	Class 1 EN 11611
ARCO ELÉCTRICO / ELECTRIC ARC		ATPV: 9,6 cal/cm ² ELIM: 8,6 cal/cm ² 4kA APC I	No tested 4kA APC I EN 61482-1-1 EN 61482-1-2
ANTIESTÁTICO / ANTISTATIC		Pass	Pass EN 1149/3/5
ANTIÁCIDO / ANTIACID (opcional/optional)*		Pass	No tested EN 13034
ALTA VISIBILIDAD / HIGH VISIBILITY ¹		Pass ¹	Pass ¹ EN 20471

*Prendas antiácidas: polimerizar 2 minutos a 160°C o aditivar con acabado fluorocarbonado tras cada ciclo de lavado.
Antacid garments: polymerize 2 minutes at 160°C or add fluorocarbon finish after each washing cycle.

¹Condiciones de lavado EN 6330 (60°C) / Washing instructions EN 6330 (60°C)


825 Xispal RS

Rev. 7

Sectores recomendados / Recommended use:



Petróleo y gas
Oil & Gas



Electricidad
Electricity



Petroquímicas
Petrochemistry



Fundiciones (Fe/Al)
Foundries (Fe/Al)

Normativas para prenda / Standard for garments:



Instrucciones de lavado EN 15797 (75°C) / Washing instructions EN 15797 (75°C):



Colores disponibles / Available colors:



Amarillo HV
HV Yellow



Rojo 30
Red 30



Gris 80
Grey 80



Gris 82
Grey 82



Azulina 50
Royal Blue 50



Marino 70
Navy Blue 70



Marino 60
Navy Blue 60



STANDARD
100

2008AN2098
AITEK