

427 Rip-Stop Tecvin

Rev. 0

Recommended end-use /
Uso recomendado:
JACKET, PANTS & COVERALL
FORESTMEN GARMENTS /
CAMISOLA, PANTALÓN Y
OVEROL, PRENDAS PARA
FORESTALES

Composition / Composición:
60% Viscosa FR / FR Viscose
39% M-Aramida / M-Aramide
1% Antiestático / Antistatic



427 Rip-Stop Tecvin

LIGAMENT LIGAMENTO	Twill Sarga	
WEIGHT (oz sq yd) PESO (gr/m²)	7,96 ± 5% 270 ± 5%	UNE 40339
WIDTH (in) ANCHO (cm)	63 ± 1,2 160 ± 3	
PILLING MARTINDALE (5.000 cycles)	4	UNE-EN 12945-2
WASHING SHRINKAGE ENCOGIMIENTO AL LAVADO	5%	AATCC 135 (3, IV, A, iii)
PRE-TREATMENT PRETRATAMIENTO	Standard requirements	
HEAT RESISTANCE RESISTENCIA AL CALOR	Pass	ASTM F2894 (NFPA 2112)
VERTICAL FLAMMABILITY INFLAMABILIDAD VERTICAL	Pass	ASTM D6413 (NFPA 2112)
HEAT TRANSFER PERFORMANCE (TPP/HTP) TRANSFERENCIA DE CALOR	Pass	ASTM F2700 (NFPA 2112)
THERMO TEX TEST / ENSAYO DE THERMO TEX (%) (Predicted total area of burn injury (average 2nd & 3rd degree))	7,4	ASTM F1930 (NFPA 2112)
FOREST MEN (after 50w *) FORESTAL	Pass	EN 15384
ANTISTATIC (*) ANTIESTÁTICO	Pass	EN 1149/3/5
TENSILE STRENGTH (N W x F) (*) RESISTENCIA A LA TRACCIÓN (N U x T)	990 ± 5% 730 ± 5%	UNE-EN ISO 13934-1
TEAR RESISTANCE (N W x F) (*) RESISTENCIA AL RASGADO (N U x T)	80 ± 5% 65 ± 5%	UNE-EN 13937-2

(*) Pre-treatment EN6330 (60°C)

427 Rip-Stop Tecvin

Rev. 0

Recommended use / Sectores recomendados:



Oil & Gas
Petróleo y gas



Forestal
Forestmén

Standard for garments / Normativas para prenda:



Washing instructions: AATCC 135 (3, IV, A, iii) Washing Temp. (120°F) Drying Temp. (149°F)
Instrucciones de lavado: AATCC 135 (3, IV, A, iii) Temp. lavado (49°C) Temp. Secado (65°C)



Available colors / Colores disponibles:



Yellow 1013
Amarillo 1013



Green 1016
Verde 1016



Navy Blue 60
Marino 60

* Melange o full dyed / Opciones vigoré o plancha

We have a special color dyeing service and a minimum quantity of 600 m.
Ofrecemos el servicio de tintar colores especiales y una cantidad mínima de 600 m por color.