

844 Denim Xispal RS

Rev. 0

Uso recomendado /
Recommended end-use:
CHAQUETA Y PANTALÓN
/ JACKET & PANTS

Composición / Composition:
61% Algodón / Cotton
31% Acrílica modificada tipo-F / Modified acrylic fibre type-F
8% Viscosa / Viscose




844 Denim Xispal RS

LIGAMENTO / LIGAMENT		Sarga / Twill	
PESO / WEIGHT (gr/m²)		440 ± 5%	UNE 40339
ANCHO / WIDTH (cm)		160 ± 3	
PILLING MARTINDALE (5.000 cycles)		5	EN 12945-2
ENCOGIMIENTO AL LAVADO WASHING SHRINKAGE		5%	UNE-EN ISO 6330
PRETRATAMIENTO / PRE-TREATMENT		Standard requirement	
RESISTENCIA A LA TRACCIÓN (N U x T) TENSILE STRENGTH (N W x F)		1230 ± 5% 880 ± 5%	UNE-EN 13934-1
INFLAMABILIDAD INFLAMMABILITY		A1-A2	EN 15025 (EN 11612)
CALOR CONVECTIVO CONVECTIVE HEAT		B1	ISO 9151
CALOR RADIANTE RADIANT HEAT		C1	ISO 6942
RESIST. A GRAN SALPICADURA. BIG SPLASH RESIST.	ALUMINIUM (780°C)	D2	ISO 9185
	IRON (1400°C)	E3	ISO 9185
CALOR POR CONTACTO CONTACT HEAT		F1	EN ISO 12127-1
ARCO ELÉCTRICO / ELECTRIC ARC		ATPV: Category II 4kA APC I	ASTM F1959 (NFPA 70 E) EN 61482-1-2

844 Denim Xispal RS

Rev. 0

Sectores recomendados / Recommended use:



Electricidad
Electricity



Petroquímicas
Petrochemistry



Fundiciones (Fe/Al)
Foundries (Fe/Al)

Normativas para prenda / Standard for garments:



Instrucciones de lavado EN 6330 (60°C) / Washing instructions EN 6330 (140°F):



*Evitar utilizar suavizantes / Avoid using softeners

Colores disponibles / Available colors:



Denim Blue

Recomendaciones para confección / Recommendation for making:

Utilizar agujas de punta redonda / Use round tips needles