

844 Denim Xispal RS

Rev. 2

Recommended end-use /
Uso recomendado:
JACKET & PANTS /
CAMISOLA Y PANTALÓN

Composition / Composición:

61% Cotton / Algodón

31% Modified acrylic fibre type-F / Acrílica modificada tipo-F

8% Viscose / Viscosa




LIGAMENT LIGAMENTO	Twill Sarga	
WEIGHT (oz sq yd) PESO (gr/m ²)	12,98 ± 5% 440 ± 5%	EN 12127
WIDTH (in) ANCHO (cm)	63 ± 1,2 160 ± 3	
PILLING MARTINDALE (5.000 cycles)	4 5	ASTM D3512 EN ISO 12945-2
WASHING SHRINKAGE ENCOGIMIENTO AL LAVADO	5%	AATCC 135 (3, IV, A, iii)
ASTM		
PRE-TREATMENT PRETRATAMIENTO	Standard requirement	
TENSILE STRENGTH (N W x F) RESISTENCIA A LA TRACCIÓN (N U x T)	919 ± 5% 676 ± 5%	ASTM D5034
ELMENDORF TEAR (N W x F) DESGARRO ELMENDORF (N U x T)	39 ± 5% 34 ± 5%	ASTM D1424
VERTICAL FLAMMABILITY Char length (in) After flame (s)	Pass	ASTM D6413 (ASTM F1506)
ELECTRIC ARC ARCO ELÉCTRICO	ATPV: Category II	ASTM F1959 (NFPA 70 E)
UNE EN*		
PRE-TREATMENT PRETRATAMIENTO	Standard requirement	
TENSILE STRENGTH (N W x F) RESISTENCIA A LA TRACCIÓN (N U x T)	1400 ± 5% 990 ± 5%	EN ISO 13934-1
INFLAMMABILITY / INFLAMABILIDAD	A1-A2	EN ISO 15025 (EN
CONVECTIVE HEAT / CALOR CONVECTIVO	B1	EN ISO 9151
RADIANT HEAT / CALOR RADIANTE	C1	EN ISO 6942
BIG SPLASH RESIST. RESIST. A GRAN SALPICADURA	ALUMINIUM (1436°F / 780°C)	D2 EN ISO 9185:2007
	IRON (2550°F / 1400°C)	E3 EN ISO 9185:2007
CONTACT HEAT / CALOR POR CONTACTO	F1	EN ISO 12127-1
WELDING / SOLDADURA	Class 1	EN ISO 11611

*Washing instructions EN ISO 6330 (140°F) / Instrucciones de lavado EN ISO 6330 (60°C):

844 Denim Xispal RS

Rev. 2

Recommended use / Sectores recomendados:



Electricity
Electricidad



Petrochemistry
Petroquímicas



Foundries (Fe/Al)
Fundiciones (Fe/Al)




Welding
Soldadura

Standard for garments / Normativas para prenda:



Washing instructions: AATCC 135 (3, IV, A, iii) Washing Temp. (120°F) Drying Temp. (149°F)
Instrucciones de lavado: AATCC 135 (3, IV, A, iii) Temp. lavado (49°C) Temp. Secado (65°C)



Available colors / Colores disponibles:



Denim Blue

Recommendation for making / Recomendaciones para confección:

Use round tips needles / Utilizar agujas de punta redonda